

ITEM #	UBR PART #	PREVIOUS DESCRIPTION	# OF PLY	COVER DURO SHORE A	COVER THICK (INCH)	OAT (INCH)	MAX SLAB WIDTH (INCH)	TENSION TO 1% ELONGATION (LBS/PIW)	Operating Temp (F)	WEIGHT IN LBS PER SQ FT	MIN PULLEY DIA (Inch)
<b>NON-FRAY</b>											
100130	U-SI/1ENF UR M White	T100/HR Matt White	1	85 A	0.008	0.039	59	17 LBS/PIW	212 °	0.20	0.31
130210	U92/2 ENF M White	TT12 Matt White	2	92 A	0.008	0.051	126	40 LBS/PIW	212 °	0.31	0.47
130235	U92/2ENF-AS M White	TT12 AS Matt White	2	92 A	0.008	0.051	126	40 LBS/PIW	212 °	0.31	0.47
130201	U92/2ENF-AS G White	TT12 AS Gloss White	2	92 A	0.008	0.051	126	40 LBS/PIW	212 °	0.31	0.47
130251	U85/2ENF-AS G WHITE	TT12U AS Gloss White	2	85 A	0.008	0.051	126	40 LBS/PIW	176 °	0.31	0.47
130206	U92/2ENF-AS M Blue	TT12 AS Matt Blue	2	92 A	0.008	0.051	126	40 LBS/PIW	212 °	0.31	0.47
130245	U-SI/2ENF UR M White	TT12/HR	2	85 A	0.008	0.071	59	40 LBS/PIW	212 °	0.37	0.80
130601	UU85/2ENF NPY M BLUE	TT162 Matt Blue	2	85 A	0.008	0.083	126	40 LBS/PIW	212 °	0.47	1.18
130606	UU85/2 ENF NPY M WHITE	TT162 Matt White	2	85A	0.008	0.083	126	40 LBS/PIW	212 °	0.47	1.18
130265	U85/2KENF G White	TT173/U White	2	85 A	0.008	0.098	118	28 LBS/PIW	176 °	0.45	0.40
130266	U85/2 KENF G White Thin (1.8)	TT173/U White thin	2	85 A	0.008	0.071	118	28 LBS/PIW	176 °	0.37	0.40
<b>AM PLUS</b>											
130406	AM-U92/2ENF-AS G White	TT12 AM Plus Gloss White	2	92 A	0.008	0.051	126	40 LBS/PIW	212 °	0.27	0.47
130401	AM-U92/2ENF-AS M Blue	TT12 AM Plus Matt Blue	2	92 A	0.008	0.051	126	40 LBS/PIW	212 °	0.27	0.47
130605	AM-UU85/2ENF NPY M White	TT162AM Plus Matt White	2	85 A	0.008	0.083	126	40 LBS/PIW	212 °	0.47	1.18
130600	AM-UU85/2ENF NPY M Blue	TT162 AM Plus Matt Blue	2	85 A	0.008	0.083	126	40 LBS/PIW	212 °	0.47	1.18
<b>COVERED MONOFILAMENTS</b>											
100122	U85/1E-AS M White	T04U/AS Matt White	1	85 A	0.008	0.023	126	23 LBS/PIW	176 °	0.12	0.16
100121	U85/1E M White	T04U Matt White	1	85 A	0.008	0.023	126	17 LBS/PIW	176 °	0.12	0.16
100120	U85/1E G White	T04U Gloss White	1	85 A	0.008	0.023	126	17 LBS/PIW	176 °	0.12	0.16
100105	U85/1E G Green	T04 Gloss Green	1	85 A	0.008	0.023	126	23 LBS/PIW	212 °	0.12	0.16
100100	U85/1E G Amber	T04 Gloss Amber	1	85 A	0.008	0.023	126	23 LBS/PIW	212 °	0.12	0.16
140305	U85/1EC G White	T15/PX	1	85 A	0.006	0.045	126	23 LBS/PIW	176 °	0.23	0.31
100210	U92/2E M White	TT140 Matt White	2	92 A	0.008	0.051	126	40 LBS/PIW	212 °	0.29	1.00
100230	U92/2E-AS M White	TT140AS Matt White	2	92 A	0.008	0.051	126	45 LBS/PIW	212 °	0.29	1.00
100225	U92/2E-AS M Green	TT140AS Matt Green	2	92 A	0.008	0.051	126	45 LBS/PIW	212 °	0.29	1.00
100270	U92/2EXH M White	TT160 Matt White	2	92 A	0.008	0.059	126	69 LBS/PIW	212 °	0.35	1.00
100255	U92/2E-AS G Clear	TT191/ASH Clear	2	92 A	0.020	0.071	126	40 LBS/PIW	212 °	0.41	1.57
100250	U92-XH/2E-AS G Clear	TT191/AS/XH 2mm Clear	2	92 A	0.020	0.079	126	40 LBS/PIW	212 °	1.57	1.57
100400	UU85/2E M WT	TT122	2	85 A	0.008	0.059	78.75	40 LBS/PIW	212 °	0.35	1.00
100500	U92/3E G WT	3T30	3	92 A	0.008	0.087	78.75	69 LBS/PIW	212 °	0.49	3.94
<b>BARE/FRICTION COATED MONO-FABRICS</b>											
100605	U0/1E Green	T05JC Green	1	N/A	N/A	0.020	86	17 LBS/PIW	212 °	0.05	0.39
100260	U0/2E Green/White	TT59	2	N/A	N/A	0.039	126	40 LBS/PIW	212 °	0.18	0.79
100720	U0/2E-AS G Clear	TT120AS FW Clear	2	N/A	N/A	0.037	126	29 LBS/PIW	212 °	0.18	1.00
100715	U0/2E-AS Gray	TT120/X/AS Black	2	N/A	-	0.057	126	34 LBS/PIW	212 °	0.30	1.00
<b>BARE/FRICTION COATED SPUN FABRICS</b>											
100805	U0/2EC Green/White	TC13NM	2	N/A	-	0.051	126	34 LBS/PIW	212 °	0.23	0.31
110305	U0/2ES-0 White	ST200 FxB White	2	N/A	-	0.055	126	34 LBS/PIW	176 °	0.25	0.39
110310	U0/2ES White	ST200 FxF White	2	N/A	-	0.055	126	34 LBS/PIW	176 °	0.25	0.39
110300	U0/2ES White Rib	ST200 BxB Rib White	2	N/A	-	0.067	126	29 LBS/PIW	176 °	0.29	0.39
110400	U0/3ES White Rib	ST300 BxB Rib White	3	N/A	-	0.098	126	46 LBS/PIW	176 °	0.43	1.97
110405	U0/3ES White	ST300 FxF White	3	N/A	-	0.094	126	46 LBS/PIW	176 °	0.45	1.97

ITEM #	UBR PART #	PREVIOUS DESCRIPTION	# OF PLY	COVER DURO SHORE A	COVER THICK (INCH)	OAT (INCH)	STD SLAB WIDTH (INCH)	TENSION TO 1% ELONGATION (LBS/PIW)	Operating Temp (F)	WEIGHT IN LBS PER SQ FT	MIN PULLEY DIA (Inch)
<b>COVERED SPUN FABRICS</b>											
110100	U85/1ES M White	ST100/U Matt White	1	85 A	0.008	0.031	126	17 LBS/PIW	176 °	0.16	0.24
110110	U85/1ES G White	ST100/U Gloss White	1	85 A	0.008	0.031	126	17 LBS/PIW	176 °	0.16	0.24
110200	U85/2ES M White	ST200/U Matt White	2	85 A	0.008	0.063	126	34 LBS/PIW	176 °	0.33	0.39
110210	U-SI/2EC UR M White	ST200HR Matt White	2	85 A	0.008	0.063	59	34 LBS/PIW	212 °	0.33	0.39
<b>COTTON FABRICS</b>											
140300	0/1EC White	DC235RM	1	N/A	-	0.049	94	23 LBS/PIW	176 °	0.14	0.24
140210	U0/1EE White	T22/CC White	1	N/A	N/A	0.087	104	26 LBS/PIW	212 °	0.33	0.60
140100	0/2C-0 Cotton Fine	212 TCW	2	N/A	-	0.059	126	23 LBS/PIW	212 °	0.29	0.31
140200	0/2EC-0 Pet/Cotton Bare White	SPC 20C	2	N/A	-	0.087	86	17 LBS/PIW	176 °	0.43	1.97
140205	0/2EC-0 Pet/Cotton White	SPC 25	2	N/A	-	0.098	86	17 LBS/PIW	176 °	0.47	1.97
<b>PROFILE COVERS</b>											
120105	U85/1E Amber Harlequin	T04 Amber Harlequin	1	85 A	0.008	0.028	61	23 LBS/PIW	212 °	0.14	0.31
120110	U85/1E-AS White HB	T11/U Heartbeat	1	85 A	0.008	0.039	78	23 LBS/PIW	176 °	0.16	0.31
120100	U92/2E White NPW	T/NPW Knobby Top	2	85 A	0.036	0.091	63	34 LBS/PIW	212 °	0.35	1.00
120225	U85/2E White RTP	TT20/RP	2	85 A	0.036	0.087	78	34 LBS/PIW	212 °	0.39	0.79
120215	U85/2E White NPY	TT140/F	2	85 A	0.024	0.055	122	40 LBS/PIW	212 °	0.29	1.00
120221	U85/2E White RIB	TT140/U Lateral Rib	2	85 A	0.036	0.075	67	40 LBS/PIW	176 °	0.39	1.00
<b>OTHER CONSTRUCTIONS</b>											
320110	S0/1 E-AS Green	NEW	1	N/A	-	0.030	64	23 LBS/PIW	212 °	0.14	0.31
320100	SI/1E G White	T063 White	1	85 A	0.008	0.030	122	17 LBS/PIW	212 °	0.14	0.20
190100	NT90 White Elastic	NT90	1	92 A	0.036	0.036	61	2 LBS/PIW	140 °	0.23	0.20
320200	SI/2E G White	TT133 White	2	85 A	0.008	0.059	118	45 LBS/PIW	212 °	0.33	1.00
320205	SI/2E AS G Blue	TT133/AS Blue	2	85 A	0.008	0.059	118	34 LBS/PIW	212 °	0.33	1.00
320210	SI/2E-AS M White	TT120AS/SI	2	N/A	-	0.057	78	34 LBS/PIW	212 °	0.30	1.00
310100	NR/2E-AS Green	TT23/AS/GPR GR	2	83 A	0.020	0.091	78	40 LBS/PIW	212 °	0.45	1.57

**PU - EXAMPLE**

**AM-UU92/2ENF-AS NPY M Blue**

