



UNIVERSAL BELTING RESOURCE

"Working Through Distribution"


2 Paisley Park
 Carmichaels PA 15320
 800-928-9995
 customers@ubelting.com
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

100225

U92/2E AS M GREEN

Splice (options)	Pressure (psi)	Temperature		Press Time (min)	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Splice - Water Cooled	35	170° C 338° F	150° C 302° F	30 seconds	Top	PU Foil	N/A
Finger Splice - Carbon Fiber High Speed	15	170° C 338° F	150° C 302° F	30 seconds	Top	PU Foil	N/A
Mechanical Lacing		UCM 36 X SP (Clipper)					
		#00 (Alligator)					
Notes: Use Matt Release on Top							
Recommended Joining Procedure: Finger Splice							



Single Finger
 -Prepared or Finished