



UNIVERSAL BELTING RESOURCE

"Working Through Distribution"


2 Paisley Park
 Carmichaels PA 15320
 800-928-9995
 customers@ubelting.com
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

100231

U85/2E-AS G White

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Splice - Water Cooled	30	160° C 320° F	150° C 302° F	40 Seconds	Top	PU Foil	N/A
Mechanical Lace							
Note: Gloss release on Top							
Recommended Joining Procedure: Finger Splice							



Single Finger
 -Prepared or Finished