



UNIVERSAL BELTING RESOURCE

"Working Through Distribution"


2 Paisley Park
 Carmichaels PA 15320
 800-928-9995
 customers@ubelting.com
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

110210

U-SI/2EC M WHITE

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Splice -Water Cooled	35	165° C 329° F	160° C 320° F	No Stand Time	None	N/A	N/A
Finger Splice - Carbon Fiber High Speed	15	160° C 320° F	160° C 320° F	10 Seconds	None	N/A	N/A
Mechanical Lace		36SP, UCM 36SP (Clipper)					
		# 00 (Alligator)					
Rough Teflon bottom - matt release paper on top							
Recommended Joining Procedure: Finger Splice							



Single Finger
 -Prepared or Finished