



UNIVERSAL BELTING RESOURCE

"Working Through Distribution"

2 Paisley Park
 Carmichaels PA 15320
 800-928-9995
 customers@ubelting.com
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

200281

2P120/10/0 H AS G GREEN

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Over Finger	35	177°C 350°F	177°C 350°F	4 minutes	Top	PVC	N/A
Lap Splice	25	177°C 350°F	177°C 350°F	4 minutes	Top	PVC	N/A
Mechanical Lace		# 36 (Clipper)					
		Staple # 62 (Alligator)					
Note:							
Recommended Joining Procedure: Lap Splice							

