



UNIVERSAL BELTING RESOURCE

"Working Through Distribution"


2 Paisley Park
 Carmichaels PA 15320
 800-928-9995
 customers@ubelting.com
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

200400

1PN80/06/06 WHITE

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Splice - Water Cooled	30	170° C 338° F	170° C 338° F	2 Minutes	Top	PVC Foil	N/A
Mechanical Lacing		Not recommended					
		Not recommended					
Note: Matt release paper on top/rough Teflon bottom							
Recommended Joining Procedure: Finger Splice							



Single Finger
 -Prepared or Finished