



**UNIVERSAL BELTING RESOURCE**

"Working Through Distribution"

# 2 Paisley Park  
 Carmichaels PA 15320  
 800-928-9995  
 customers@ubelting.com  
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

**200706**

**2PS80/0/0 AS BK**

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger over Finger Finger over Lap	30	170° C 338° F	170° C 338° F	2 minutes	Center	PVC	N/A
Lap Splice	30	170° C 338° F	170° C 338° F	2 minutes	Center	PVC	N/A
Mechanical Lace		# 36 SP (Clipper)					
		# 00 (Alligator)					
<b>Note: Rough Teflon on bottom, 1ply silicone on top</b>							
<b>Recommended Joining Procedure: Lap Splice</b>							

