



UNIVERSAL BELTING RESOURCE

"Working Through Distribution"


2 Paisley Park
 Carmichaels PA 15320
 800-928-9995
 customers@ubelting.com
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

100250

U92-EX/2E - AS G CLEAR

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Splice - Water Cooled	20	170° C 338° F	165° C 329° F	1 minute	Top	PU Foil	N/A
Finger Splice - Carbon Fiber High Speed	15	175° C 347° F	165° C 329° F	30 seconds	Top	PU Foil	N/A
Mechanical Lacing		#36 Series (Clipper)					
		#1 (Alligator)					
Note: Release paper top/rough Teflon paper bottom							
Recommended Joining Procedure: Finger Splice							



Single Finger
 -Prepared or Finished