



UNIVERSAL BELTING RESOURCE

"Working Through Distribution"


2 Paisley Park
 Carmichaels PA 15320
 800-928-9995
 customers@ubelting.com
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

100260

U0/2E GREEN/WHITE

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Splice - Water Cooled	19	165° C 329° F	165° C 329° F	1 minute	Bottom	PU Foil	N/A
Finger Splice - Carbon Fiber High Speed	15	165° C 329° F	165° C 329° F	30 seconds	Bottom	PU Foil	N/A
		UCM 36 x SP (Clipper)					
		#00 (Alligator)					
Note: Rough Teflon on bottom / Silicone on top							
Recommended Joining Procedure: Finger splice							



Single Finger
 -Prepared or Finished