



UNIVERSAL BELTING RESOURCE

"Working Through Distribution"

2 Industrial Park Road
 Carmichaels PA 15320
 800-928-9995
 customers@ubelting.com
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

100405

UU85/2E-AS Matt/Gloss White

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Splice - Water Cooled	20	165° C 329° F	165° C 329° F	30 Seconds	Top 2 pcs	PU	N/A
Mechanical Lace		# 36 Series (Clipper)					
		# 1 (Alligator)					
Notes: Matt release paper top / Gloss release bottom							
Recommended Joining Procedures: Finger Splice							

