



**UNIVERSAL BELTING RESOURCE**

"Working Through Distribution"


# 2 Paisley Park  
 Carmichaels PA 15320  
 800-928-9995  
 customers@ubelting.com  
 www.universalbelting.com

This sheet is a guideline only. Every press is a little different. We recommend that you do a test splice with your press before attempting the actual belt splice.

**200405**

**1PN80/04/04 F GREEN**

Splice (options)	Pressure (psi)	Temperature		Press Time	Foil (position)	Foil (type)	Skive Length (inch)
		TOP	BOTTOM				
Finger Splice - Water Cooled	30	170° C 338° F	170° C 338° F	2 Minutes	Top	PVC Foil	N/A
Mechanical Lacing	Not recommended						
	Not recommended						
<b>Note: Matt release paper on top/rough Teflon bottom</b>							
<b>Recommended Joining Procedure: Finger Splice</b>							



Single Finger  
 -Prepared or Finished